



# Data Sheet

a.c. ter kuile b.v.  
P.O. Box 75 7500 AB Enschede Nederland  
Kneedweg 35 7511 CB Enschede

Phone: +31(53) 4316841  
E-mail: [actk@actk.nl](mailto:actk@actk.nl)  
[www.actk.nl](http://www.actk.nl)  
V.A.T/B.T.W. nr. NL 004004279B01

<b>Article name:</b>	<b>TK 021-450</b>
Width:	150 cm
Colours:	white, black
Article description:	Polyester single jersey knit multidirectional stretch
Application:	Suitable for all kinds of fabrics, for front parts, lapels and collars.
Composition:	100% polyester
Weight:	± 44 grs/m <sup>2</sup>
type of coating:	Co-Polyamide double dot CP 90
fusing temperature:	130-140 °C
pressure dial setting:	300 - 500 gr/cm <sup>2</sup> (flatbed press) 3-4 bar (continuous press)
Duration:	10 – 15 seconds
After care:	washing 40°C dry cleaning allowed (P)



## Fusing recommendations

### Temperature

The recommended temperature is the heat which is available for fusing between the platens or rollers of a fusing press rather the reading on the temperature dial. Should a digital pyrometer not be available to check the temperature, the use of thermo papers is recommended.

### Pressure

A majority of conveyor-type electrically-heated presses indicate the pressure as line pressure or dial pressure. The equivalent pressure exerted on the press bed (buck pressure) is calculated as roughly one twentieth of the line pressure. For other types of presses, operators should consult their press supplier for conversion factors.

### Time

The specified fusing time is that in which fusing is actually taking place, i.e. when the platens are closed (flat bed) or when the garment part is in the main heating zone (conveyor type). The overall time should, therefore be adjusted by the timing dial to allow for these conditions.

### Fusing records

For optimum results it is essential that the press operators carry out periodic checks on each of the above three parameters and a record kept of all readings.

### Testing:

Fusing conditions are given as a guide and should be varied to suit individual presses and top fabrics.

Tests to evaluate the compatibility of the interlining and top fabric, both before and after washing and/or dry cleaning, are recommended before proceeding to bulk production.